
# TECHNICAL DATA SHEET

# DAB12-33





### **Specifications**


	Dimensions mm - kg						Dimensions Inches - Ibs						Cold Cranking Amps		
			Height	Height	Height				Height	Height	Height		20°C	0°C	-18°C
	Length	Width	Auto	Insert	Battery	Weight	Length	Width	Auto	Insert	Battery	Weight	(68°F)	(32°F)	(0°F)
DAB12-33	196	131	1	151	160	10.4	7.70	5.16	1	5.94	6.30	21.84	353	258	166

			Reserve Capacity - Mins					Capacity - Ampere Hour*						
	Volts	Thread size mm	75 Amps	25 Amps	20 Amps	15 Amps	8 Amps	100 Hr	48 Hr	20 Hr	10 Hr	5 Hr	3 Hr	1 Hr
DAB12-33	12	6	7	32	54	79	177	39.1	36.7	34.0	32.0	28.0	25.7	20.5

#### **Dimensions**







## **Applications**









CYCLIC


**STATIONARY** 

**SOLAR** 

## **TECHNICAL DATA SHEET**

**DAB12-33** 

#### Charging



Nominal voltage 6 & 12 volts

Design life 12 Years @ 20°C

Operating temperature -10 °C to 45°C

Grid alloy Calcium / Tin lead alloy

Plates Flat pasted

Separator Absorbant Glass Mat
Active Material Very high purity lead
Case and cover ABS (VO on request)
Charge voltage Float 2.27 - 2.30 VPC @ 20°C

Cycling 2.40 @ 20°C

Max. 2.4 VPC Max ripple 3.5%

Charging V

Electrolyte Sulphuric acid analytical grade

purity

#### **CHARGING CHARACTERISTICS**

Floating - The optimum float voltage for a battery is temperature dependant, at 15 -  $24^{\circ}$ C the recommended value is 2.27 - 2.30V. It is recommended that battery installation sites are temperature controlled, however float voltage can be increased or decreased to compensate for temperature variations. Adjustment is calculated at +/- 3 mV per degree C.

Operating Temperature	Recommended Applied Float Voltage VPC						
0-9	2.33-2.35						
10-14	2.30-2.33						
15-19	2.27-2.30						
20-24	2.27-2.30						
25-29	2.25-2.27						
30-34	2.23-2.25						
35-40	2.21-2.23						

The most suitable charging method for battery life and performance is the constant voltage method with a limited initial current, usually limited to a maximum of  $\rm C_{20}/4$ . For cyclic use we specify a short constant current phase at the end of normal charging, consult us for further details.

Charging - To obtain maximum cycle life from your battery, it is important that a suitable charging profile is used. For information about our range of chargers and our recommended charging profile, please contact us.