Weller





source images

WSW SCN M1 0,3mm, 100g, Sn0,6Cu0,05Ni3,5%

Product number: T0051402899 SCN M1 Solder Wire, Ø 0,3mm, 100g

- Diameter: 0.3 mm / 0.012 inch, Weight: 100 g / 3.527 oz
- Alloy Sn99.3Cu0.6Ni0.05, Flux content 3.5%
- Silver free alloy = cost effective
- Guaranteed 100% continuous flux core
- Higher strength due to nickel compared to other silver-free alloys.
- Reduced Fe leaching to increase tip life time and reduce tip consumption by up to 70%.
- Very fast wetting even on difficult surfaces, as dirty and oxidized materials
- High soldering temperatures possible with excellent melting characteristics
- Solder joint shines (perfect optics)
- Reduced splash of flux & No-Clean flux

The Perfect Solder Joint.

Designed to enhance the quality of all your soldering jobs, Weller WSW increases productivity, and optimizes your soldering performance. With a guaranteed 100% continuous flux core, combined with pure first metal melting, WSW enables long-term, highly durable solder joints without cracking, even on difficult surfaces.

WSW SOLDER WIRE THE PERFECT **PERFORMANCE** & SOLDER JOINT PRODUCTIVITY Optimized performance with a guaranteed and Weller consistent 100% continuous flux core N3.0AG0.5CU WSW SAC M1 T0051386399 LOT 21.06.01 SIZE 0.8mm **LOW TOTAL COST TIP WETTING** RoHS **OF OWNERSHIP** Fast and homogeneous wetting due to Up to 70% less reduced tip consumption and provide 100% continuous flux core a low total cost of ownership by saving labor time & ressources due a higher productivity **REDUCED SPLASH QUALITY** Increase direct user safety as well as workplace cleanliness **SOLDER JOINTS** Long-term, highly durable soldering joints FLOW & HEAT PERFORMANCE that will not crack, even on difficult surfaces Patented alloys guarantees optimal results MAXIMUM FLEXIBILITY Wide range of alloys and fluxes as well as various wire diameter

Weller[®]

| Technical Data | |
|---|----------------------|
| | |
| Alloy | Sn0.6Cu0.05Ni |
| Solder wire Ø mm | 0.3 |
| Solder wire Ø Inch | 0.011 |
| Temperature range °C | 228-229 |
| Temperature range °F | 442,4-444,2 |
| Flux proportion | 3.5% |
| Total length solder wire in yard | 255.26 |
| Reduced Splash | on |
| Use of 100% first melt for production | on |
| No-clean solder wire (no residual flux cleaning necessary | on |
| Halide containing | on |
| Halide free | |
| WSW category | Leadfree solder wire |
| 100% continuous flux core | on |
| Flux classification | M1 |
| Total length solder wire in m | 233.41 |
| RoHS compliant | on |
| Weight in g | 100 |
| Weight in oz | 3.527 |
| Dimensions W x L x H | 63 x 65 |

Weller Tools GmbH Carl-Benz-Straße 2 74354 Besigheim Germany Phone: +49 (0) 7143 / 580-0 Fax.: +49 (0) 7143 / 580-108 Email: info@weller-tools.com Web: www.weller-tools.com